



Introducing

Getting light, right

LUMISOL Pro



Lumisol Pro




LUMISOL Pro

Guaranteed 3 year film lifespan

Widths: Up to 14m

Thickness: 200µm





UV Stability Warranty:

3 years Almeria (160kLy)

Chemical Resistance Warranty:

3000ppm Sulphur

| Year 1 | Year 2 | Year 3 |
|---------|---------|---------|
| 1000ppm | 2000ppm | 3000ppm |

200ppm Chlorine

| Property | Test Method | Specification |
|----------------------------|------------------|---------------|
| Nominal Thickness (µm) | ISO 4593 | 200 (+/- 5%) |
| Light Transmission (%) | ASTM D1003 | ≥ 88 |
| Diffusion (%) | ASTM D1003 | 50 - 60 |
| Thermicity (%) | BS EN 13206:2001 | > 75 |
| Elongation at Break MD (%) | ASTM D882 | > 500 |
| Impact Strength (g) | ASTM D1709 | > 600 |

